P-ISSN: 1680-9300
E-ISSN: 2790-2129
Vol. (26), No. (4)
pp. 38-43

Anti-Bacterial Action of Zinc Oxide Nanoparticles against Skin Bacterial Infection

Haider Q. Raheem
DNA Research Center, University of Babylon, Al-Karamah Street - 51001, Babylon, Iraq.

Abstract:

It has been observed that metal nanoparticles containing oxides of Znic Oxide, copper, silver, nickel, iron furthermore other elements exhibit antibacterial qualities. The antibacterial action of zinc oxide nanoparticles against a variety of species of pathogenic bacteria, including Klebsiella pneumonia, Escherichia coli, Proteus vulgaris and Pseudomonas aeruginosa is examined in this study. Using dilutions of [200, 100, 50, 25, and 12.5 µg/mL], the disk diffusion test existed employed to judge the antibacterial action of Zno NPs and conclude the MIC, MBC of each isolate. Through arise in inhibition area diameter that is straight proportionate to a rise in nanoparticle concentration, Zno NPs exhibits potent wide-ranging antibacterial action against tested bacteria, even surpassing the activity of certain medications. When compared to the chosen antibiotics, P.vulgaris appeared to be the least sensitive isolate, while Pseudomonas aeruginosa demonstrated great sensitivity even at 12.5 µg/mL. P.aeruginosa, with the MBC ranging since 25 to 200 µg/mL and the MIC of Zno NPs ranging from 12. µg/mL to 50 µg/mL.It is greatly recommended consuming Zno NPs as a profitable alternate antibacterial cause particularly in handling ectopic pathogenic outbreaks deprived of attractive danger of evolving resistant bacterial isolates with antibiotics.

Keywords: Zno, Nanoparticles, Anti-Bacterial Activity, Antibiotics.

1. Introduction

Diverse kinds of metallic as well as metal oxide nanoparticles through antibacterial: action has been created appreciations to current advancements in nanotechnology. It has been observed that metal nanoparticles containing oxides of Znic Oxide, Copper, silver, nickel, iron furthermore other elements exhibit antibacterial qualities (Qi, K et al.,2017; Pachaiappan et al.,2021; Padilla-Cruz et al.,2025). Nanoparticles through a great exterior area offer a wide variety of responses with the bacterial surface because the anti-bacterial activity of the NPs remained originate to be reliant on the external area in touch through the microbe (Liao et al.,2020).

Nanoparticles (NPs) are minuscule materials with sizes ranging from one to one hundred nanometers. They were categorized according to their sizes, shapes, and other attributes. Fullerenes, metal nanoparticles, ceramic nanoparticles, and polymeric nano particles are a few of the categories. These characteristics have resulted into several home and commercial applications, including as imaging, uses in medicine, catalysis, and the environment (Kołodziejczak-Radzimska and Jesionowski, 2014).

Journal of Prospective Researches
Vol. (26), No. (4)
The paper was received on April 21, 2026; accepted on June 13, 2026; and published on October 29, 2026.
Corresponding author's e-mail: haider.qassim@uobabylon.edu.iq

10.61704/pr.655

Znicoxide nanoparticles, or ZnO-NPs, are intriguing inorganic materials (Zanet et al., 2019). These nanomaterial's have many unique characteristics, and ZnO has been thoroughly studied and shown to exhibition antibacterial inaction together with a diversity of bacteria. Furthermore, ZnO is an inexpensive, easily accessible, and biocompatible material.Furthermore, this oxide has some beneficial features over widely used Ag NPs, such as their photochemical stability and cheap production costs (Hoseinzadeh et al., 2014 ; Jiang and Cai, 2018).).

ZnO-NPs, or Zno oxide nanoparticles, are utilized in a number of sectors, including antibacterial agents, concrete, textiles, cosmetics, medicine, and cancer prevention. This is because they can cause cell death (apoptosis) and create reactive oxygen species (ROS) (Tiwari et al.,2018; Alothman and Albaqami, M. 2020).

Since several NPs have been thoroughly studied and have demonstrated promising antibacterial activity, the combination of nanotechnology besides natural science is utilized to resolve numerous biomedical complications then canister be applied successfully besides carefully in the arena of healthiness (Karekar et al.,2015). Since Zno is the most basic member of the zinc compound family also exhibits a variety of practical mental structures, counting great heat, electron relationship properties, superconductivity besides rotation diminuendos, it has garnered special attention among different metal oxide nanoparticles (Siddiqi et al.,2018; Agarwal et al.,2018; Tripathy and Sahu, 2019).

2. Materials and Methods

2.1 Nanoparticle, Culture Media, Antibiotic disks were used in this training

Nanoparticle, Culture Media, Antibiotic disks were used in this training listed in table (1).

Table 1. Nanoparticle, Culture Media, Antibiotic Disks.

Antibiotic Discs	Company
Amikacin (AK30)	Bio-analyses in Turkey
Cefotaxime (CX30)	
Ciprofloxacin (CPR5)	
Gentamicin (CN10)	
Culture media	Company
Blood agar	HIMEDIA, India
MacConkey's,	
Mueller-Hinton agar	
Nutrients agar	
Znic Oxide nanoparticles (40nm).	Zhengzhou,Dongyao Nano Materials Co., LTD, China,

2.2 Antibacterial Activity of Zno NPs

Patients that stay the Education Hospital in Hillah, Babylon province, Iraq, providing the bacterial isolates. For isolation and purification, all materials stayed cultured proceeding MacConkey's, blood agar plates for 24 to 48 hours at 37°C using normal bacteriological procedures. The Viteck 2 compact system was castoff to check each isolate. Four-gram negative bacteria isolated from skin infections (Escherichia coli, Klebsiella pneumonia, Pseudomonas aeruginosa, and Proteus vulgaris) that remained grown on slants of nutrient agar stayed employed to test the antimicrobial action of the Zno nanoparticles (Raheem et al.,2022). Was followed in the execution of the antibacterial activity. A disk diffusion examine is employed to investigate bacterial sensitivity to Zno nanoparticles or antibiotics. Zno NPs were employed in triplicate in sterilized deionized water at thinning of (200, 100,

50, 25, and 12.5) µg/mL. The bacteria were principal incubated at 4°C for 15 minutes and formerly they were incubated at 37°C for the entire night. At what time a zone of inhibition was seen (surrounding the fine following the incubation period, confident test results were scored. The inhibition zone distance was then dignified using a numerical venire caliper (CLSI, 2025).

2.3 Detection of Minimum Inhibitory Concentration and Minimum Bactericidal Concentration

To make (0.5 McFarland), the bacterial isolates existed cultured for a whole night at 37°C. After preparing a (10 ml tube of nutrient broth) medium, every taster was aseptically infected by (1ml) of the corresponding bacterial postponement (108 CFU/Ml).

In sterilized deionized water, dilutions of Zno nanoparticles (200, 100, 50, 25, and 12.5) µg/mL were made, along with a negative control that included no Zno nanoparticles. For Isolation, tests were run in triplicate. Overnight, the inoculated collections were hatched at 37°C.The visual turbidity in all tube was observed following the growth dated. The MIC for the isolates under test is the lowest concentration at which there is no turbidity. Nutrient agar plates stayed castoff to cultivate tubes that had no turbidity, and they were incubated at 37°C for the entire night.

The concentration that exhibits no growth is known as the MBC. The growing of bacterial colonies was examined (El-Fallal et al.,.2023).

3. Results and Discussion

3.1 Antibacterial Activity of Zno NPs

When tested against bacteria, Zno NPs exhibit potent broad spectrum antibacterial action. We compared the impact of various medications on isolated microorganisms.

The results in Figures (1–4) demonstrated that the chosen antibiotics were effective against every strain that was chosen, whereas the CX antibiotic exhibited the least amount of activity. With an increase in nanoparticle concentration, Zno NPs demonstrated an increase in inhibitory zone diameter that uneven outdid the act of some antibiotics.

The highest area of inhibition alongside the test bacteria was observed at a dose of 200 µg/mL. Pseudomonas aeruginosa demonstrated great sensitivity even at 12.5µg/mL, with a maximum zone of inhibition of 26 mm (Figure 4).

When compared to the chosen antibiotics, P.vulgaris is the isolate that is least sensitive (Figure 3).

In addition to releasing reactive oxygen species (ROS), which produce superoxide species and aid in the breakdown of biomolecules, Zno NPs cause an abrupt decrease in the integrity of bacterial cell membranes potential mechanisms of ZnO NPs, such as:

- Generation of Reactive Oxygen Species (ROS): including hydroxyl radicals, superoxide anions, and hydrogen peroxide. These reactive molecules induce oxidative stress within bacterial cells, leading to severe damage to essential biomolecules such as lipids, proteins, and nucleic acids Oxidative stress disrupts normal cellular metabolism, causes lipid peroxidation of the membrane, denatures enzymes, and may result in DNA fragmentation (Punjabi and Deogharkar, 2018).
- Cell Wall Disruption: Direct interaction of nanoparticles with the bacterial cell membrane leading to leakage of cytoplasmic contents: ZnO NPs can directly interact with the bacterial cell wall and cytoplasmic membrane due to their Nano scale size and high surface area. Electrostatic attraction between positively charged zinc ions and negatively charged bacterial surfaces facilitates nanoparticle adhesion to the membrane (Shanmugam et al.,2023).

This interaction alters membrane permeability and integrity, resulting in: Structural deformation of the cell wall, Formation of membrane pits or pores, Leakage of intracellular materials such as proteins, ions, and nucleic acids, Loss of membrane potential and metabolic dysfunction (Rasha et al.,2021). Another important mechanism involves the gradual dissolution of ZnO NPs and the release of zinc ions. These ions can penetrate bacterial cells and interfere with multiple physiological processes. Released zinc ions may: Inhibit enzymatic activity, Disrupt protein synthesis, Interfere with

ATP production, Alter membrane transport systems, The synergistic effect between nanoparticle surface activity and released zinc ions significantly enhances the overall antibacterial efficacy of ZnO NPs (Hameed et al.,2016; Tiwari et al.,2018).




Figure 1. Antibacterial Action of Zno Nps on E. Coli.




Figure 2. Antibacterial Action of Zno NPs on K. Pnumoniae.




Figure 3. Antibacterial Action of Zno NPs on P. Vulgaris.




Figure 4. Antibacterial Action of Zno NPs on P. Aeruginsosa.

3.2 Minimum Inhibitory and Minimum Bactericidal Concentration

According to Table (2), P.aeruginosa ,K.pneumoniae exhibited the highest sensitivity, with the MIC of Zno NPs ranging from 12.5µg/mL to 50µg/mL and the MBC ranging from 25µg/mL to 200µg/mL .

Table 2. MIC and MBC of Zno NPs for some Pathogenic Bacteria.

Bacteria Isolate	MIC µg/mL	MBC µg/mL
K. pneumonia	25	100
P. vulgaris	50	100
E. coli	50	200
P. aeruginosa	25	50

4. Conclusion

According to the study's findings, Zno NPs have a significant inhibitory besides antibacterial action on the selected pathogenic bacterial strains, which is consistent with. It is strongly advised to use Zno NPs as a cost-effective substitute antibacterial agent, mainly for treating skin infections, without running the hazard of creating bacterial strains that are resistant to antibiotics.

References

Agarwal, H., Menon, S., Kumar, S. V., & Rajeshkumar, S. (2018). Mechanistic study on antibacterial action of zinc oxide nanoparticles synthesized using green route. Chemico-Biological

Interactions, 286, 60–70. https://doi.org/10.1016/j.cbi.2018.03.008

Alothman, A. A., & Albaqami, M. D. (2020). Nano-sized Cu(II) and Zn(II) complexes and their use as a precursor for synthesis of CuO and ZnO nanoparticles: A study on their sonochemical synthesis, characterization, and DNA-binding/cleavage, anticancer, and antimicrobial activities. Applied Organometallic Chemistry, 34(10), Article e5827. https://doi.org/10.1002/aoc.5827

Clinical and Laboratory Standards Institute. (2025). Performance standards for antimicrobial susceptibility testing (35th ed., CLSI standard M100).

El-Fallal, A. A., Elfayoumy, R. A., & El-Zahed, M. M. (2023). Antibacterial activity of biosynthesized zinc oxide nanoparticles using Kombucha extract. SN Applied Sciences, 5(12), Article 332. https://doi.org/10.1007/s42452-023-05546-x

Hameed, A. S. H., Karthikeyan, C., Ahamed, A. P., Thajuddin, N., Alharbi, N. S., Alharbi, S. A., & Ravi, G. (2016). In vitro antibacterial activity of ZnO and Nd doped ZnO nanoparticles against ESBL producing Escherichia coli and Klebsiella pneumoniae. Scientific Reports, 6, Article 24312. https://doi.org/10.1038/srep24312

Hoseinzadeh, E., Alikhani, M.-Y., Samarghandi, M.-R., & Shirzad-Siboni, M. (2014). Antimicrobial potential of synthesized zinc oxide nanoparticles against gram positive and gram negative bacteria. Desalination and Water Treatment, 52(25–27), 4969–4976. https://doi.org/10.1080/19443994.2013.810356

Jiang, J., Pi, J., & Cai, J. (2018). The advancing of zinc oxide nanoparticles for biomedical applications. Bioinorganic Chemistry and Applications, 2018(1), Article 1062562. https://doi.org/10.1155/2018/1062562

Karekar, S. E., Bhanvase, B. A., Sonawane, S. H., Deosarkar, M. P., Pinjari, D. V., & Pandit, A. B. (2015). Synthesis of zinc molybdate and zinc phosphomolybdate nanopigments by an ultrasound assisted route: Advantage over conventional method. Chemical Engineering and Processing: Process Intensification, 87, 51–59. https://doi.org/10.1016/j.cep.2014.11.010

Kołodziejczak-Radzimska, A., & Jesionowski, T. (2014). Zinc oxide—From synthesis to application: A review. Materials, 7(4), 2833–2881. https://doi.org/10.3390/ma7042833

Liao, C., Jin, Y., Li, Y., & Tjong, S. C. (2020). Interactions of zinc oxide nanostructures with mammalian cells: Cytotoxicity and photocatalytic toxicity. International Journal of Molecular Sciences, 21(17), Article 6305. https://doi.org/10.3390/ijms21176305

Pachaiappan, R., Rajendran, S., Show, P. L., Manavalan, K., & Naushad, M. (2021). Metal/metal oxide nanocomposites for bactericidal effect: A review. Chemosphere, 272, Article 128607. https://doi.org/10.1016/j.chemosphere.2020.128607

Padilla-Cruz, A. L., Garza-Cervantes, J. A., Vasto-Anzaldo, X. G., García-Rivas, G., León-Buitimea, A., & Morones-Ramírez, J. R. (2021). Synthesis and design of Ag–Fe bimetallic nanoparticles as antimicrobial synergistic combination therapies against clinically relevant pathogens. Scientific Reports, 11, Article 5351. https://doi.org/10.1038/s41598-021-84768-8

Punjabi, K., Mehta, S., Chavan, R., Chitalia, V., Deogharkar, D., & Deshpande, S. (2018). Efficiency of biosynthesized silver and zinc nanoparticles against multi-drug resistant pathogens. Frontiers in Microbiology, 9, Article 2207. https://doi.org/10.3389/fmicb.2018.02207

Qi, K., Cheng, B., Yu, J., & Ho, W. (2017). Review on the improvement of the photocatalytic and antibacterial activities of ZnO. Journal of Alloys and Compounds, 727, 792–820. https://doi.org/10.1016/j.jallcom.2017.08.142

Raheem, H. Q., Hussein, E. F., Rasheed, A. H., & Imran, N. K. (2022). Antibacterial action of silver nanoparticles against Staphylococcus aureus isolated from wound infection. Research Journal of Pharmacy and Technology, 15(6), 2413–2416. https://doi.org/10.52711/0974-360X.2022.00401

Rasha, E., Alkhulaifi, M. M., AlOthman, M., Khalid, I., Doaa, E., Alaa, K., Awad, M. A., & Abdalla, M. (2021). Effects of zinc oxide nanoparticles synthesized using Aspergillus niger on carbapenem-resistant Klebsiella pneumonia in vitro and in vivo. Frontiers in Cellular and Infection Microbiology, 11, Article 748739. https://doi.org/10.3389/fcimb.2021.748739

Shanmugam, R., Munusamy, T., Jayakodi, S., Al-Ghanim, K. A., Nicoletti, M., Sachivkina, N., & Govindarajan, M. (2023). Probiotic-bacteria (Lactobacillus fermentum)-wrapped zinc oxide nanoparticles: Biosynthesis, characterization, and antibacterial activity. Fermentation, 9(5), Article 413. https://doi.org/10.3390/fermentation9050413

Siddiqi, K. S., Rahman, A., Tajuddin, & Husen, A. (2018). Properties of zinc oxide nanoparticles and their activity against microbes. Nanoscale Research Letters, 13, Article 141. https://doi.org/10.1186/s11671-018-2532-3

Tiwari, V., Mishra, N., Gadani, K., Solanki, P. S., Shah, N. A., & Tiwari,

M. (2018). Mechanism of anti-bacterial activity of zinc oxide nanoparticle against carbapenem-resistant Acinetobacter baumannii. Frontiers in Microbiology, 9, Article 1218. https://doi.org/10.3389/fmicb.2018.01218

Tripathy, S., & Sahu, S. K. (2019). FtsZ inhibitors as a new genera of antibacterial agents. Bioorganic Chemistry, 91, Article 103169. https://doi.org/10.1016/j.bioorg.2019.103169

Sonnenberg, G. F., Fouser, L. A., & Artis, D. (2011). Border patrol: Regulation of immunity, inflammation and tissue homeostasis at barrier surfaces by IL-22. Nature Immunology, 12(5), 383–390. https://doi.org/10.1038/ni.2025

Zanet, V., Vidic, J., Auger, S., Vizzini, P., Lippe, G., Iacumin, L., Comi, G., & Manzano, M. (2019). Activity evaluation of pure and doped zinc oxide nanoparticles against bacterial pathogens and Saccharomyces cerevisiae. Journal of Applied Microbiology, 127(5), 1391–1402. https://doi.org/10.1111/jam.14407